

	Type	Hits	Search Text	DBs
76	IS&R	4	((("3779714") or ("4752334") or ("6174812") or ("6368967")).PN.	USPAT; USOCR
77	BRS	531	((copper or cu) with (harden\$3 or hardness)) and interconnect\$4	USPAT
78	BRS	23	((copper or cu) with (harden\$3 or hardness)) with interconnect\$4	USPAT
79	BRS	23	((copper or cu) with (harden\$3 or hardness)) with interconnect\$4	USPAT
80	BRS	607	((copper or cu) with (harden\$3 or hardness)) and interconnect\$4	USPAT
81	BRS	27	((copper or cu) with (harden\$3 or hardness)) with interconnect\$4	US-PGPUB; EPO; JPO; DERWENT; IBM_TDB
82	BRS	281	((("257").CLAS.) or (("438").CLAS.)) and (((copper cu) with (beryllium be)) and (substrate) and (diffusion barrier))	USPAT
83	BRS	129	((("257").CLAS.) or (("438").CLAS.)) and (((copper cu) with (beryllium be)) and (substrate) and (diffusion barrier))	US-PGPUB; EPO; JPO; DERWENT; IBM_TDB
84	BRS	1085	((copper cu) with (beryllium be)) and (substrate) and (diffusion barrier)	USPAT
85	BRS	85	((copper or cu) with (harden\$3 or hardness)) with (similar match matching)	USPAT
86	BRS	183	((copper or cu) with (harden\$3 or hardness)) with (similar match matching)	US-PGPUB; USOCR; EPO; JPO; DERWENT; IBM_TDB
87	IS&R	4304	(257/751-753,758,759,761-767).CCLS.	USPAT
88	BRS	1	S87 and S88	USPAT
89	BRS	446	((copper cu) with (beryllium be)) with (harden\$3 or hardness)	USPAT
90	IS&R	2635	(438/633,514,542,549,433,440,447,449,687).CCL S.	USPAT
91	BRS	13075	((copper cu) with (beryllium be))	USPAT
92	BRS	14	S90 and S91	USPAT
93	BRS	607	((copper or cu) with (harden\$3 or hardness)) and interconnect\$4	USPAT

	Type	Hits	Search Text	DBs
94	IS&R	3004	(257/751-753,758,759,761-767).CCLS.	US-PGPUB; USOCR; EPO; JPO; DERWENT; IBM_TDB
95	BRS	12845	((copper cu) with (beryllium be))	US-PGPUB; USOCR; EPO; JPO; DERWENT; IBM_TDB
96	BRS	26	S94 and S95	US-PGPUB; USOCR; EPO; JPO; DERWENT; IBM_TDB
97	IS&R	2211	(438/633,514,542,549,433,440,447,449,687).CCL S.	US-PGPUB; USOCR; EPO; JPO; DERWENT; IBM_TDB
98	BRS	10	S97 and S95	US-PGPUB; USOCR; EPO; JPO; DERWENT; IBM_TDB